

**Amendments to the Claims:**

This listing of claims will replace all prior versions and listings of claims in this application.

Please cancel claims 25 and 27 without prejudice or disclaimer.

1. (Currently Amended) A pretreatment method for cationic electrodeposition coating comprising treating a substance to be treated by a chemical conversion coating agent to form a chemical conversion coat, wherein the chemical conversion coating agent comprises: at least one member selected from the group consisting of zirconium, titanium and hafnium having a content of 50 ppm to 2000 ppm; fluorine; and at least one member selected from the group consisting of amino group-containing silane coupling agents, hydrolysates thereof and polymers thereof having a content of 50 to 500 ppm as a concentration of solid matter, said substance comprising a plurality of metal materials among the iron material, the aluminum material and the zinc material.
2. (Canceled)
3. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 1, wherein the chemical conversion coating agent contains 1 to 5,000 ppm of at least one member of a chemical conversion reaction accelerator selected from the group consisting of nitrite ion, nitro group-containing compounds, hydroxylamine sulfate, persulfate ion, sulfite ion, hyposulfite ion, peroxides, iron (III) ion, citric acid iron compounds, bromate ion, perchlorinate ion, chlorate ion, chlorite ion, ascorbic acid, citric acid, tartaric acid, malonic acid, succinic acid and salts thereof.
4. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 1, wherein the chemical conversion coating agent has a pH of 1.5 to 6.5.
5. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 1, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion and copper ion.

6. (Canceled)
7. (Canceled)
8. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 3, wherein the chemical conversion coating agent has a pH of 1.5 to 6.5.
9. (Canceled)
10. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 3, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion, and copper ion.
11. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 4, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion, and copper ion.
12. (Canceled)
13. (Canceled)
14. (Canceled)
15. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 8, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion, and copper ion.
16. (Canceled)
17. (Currently Amended) A pretreatment method for cationic electrodeposition coating comprising treating a substance to be treated by a chemical conversion coating agent to form a

chemical conversion coat, wherein the chemical conversion coating agent comprises: at least one member selected from the group consisting of zirconium, titanium and hafnium having a content of 50 ppm to 2000 ppm; fluorine; and at least one kind selected from the group consisting of amino group-containing silane coupling agents, hydrolysates thereof and polymers thereof having a content of 50 to 500 ppm as a concentration of solid matter, said substance consisting of an iron material.

18. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 17, wherein the chemical conversion coating agent contains 1 to 5,000 ppm of at least one member of a chemical conversion reaction accelerator selected from the group consisting of nitrite ion, nitro group-containing compounds, hydroxylamine sulfate, persulfate ion, sulfite ion, hyposulfite ion, peroxides, iron (III) ion, citric acid iron compounds, bromate ion, perchlorinate ion, chlorate ion, chlorite ion, ascorbic acid, citric acid, tartaric acid, malonic acid, succinic acid and salts thereof.

19. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 17, wherein the chemical conversion coating agent has a pH of 1.5 to 6.5.

20. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 17, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion and copper ion.

21. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 18, wherein the chemical conversion coating agent has a pH of 1.5 to 6.5.

22. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 18, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion, and copper ion.

23. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 19, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion, and copper ion.

24. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 21, wherein the chemical conversion coating agent contains at least one member of adhesion and corrosion resistance imparting agent selected from the group consisting of magnesium ion, zinc ion, calcium ion, aluminum ion, gallium ion, indium ion, and copper ion.

25. (Canceled)

26. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 1, wherein the chemical conversion coating agent contains substantially no phosphate ions.

27. (Canceled)

28. (Currently Amended) The pretreatment method for cationic electrodeposition coating according to Claim 17, wherein the chemical conversion coating agent contains substantially no phosphate ions.